

УДК 546.682+548.734+669.18

<https://doi.org/10.37827/ntsh.chem.2023.73.038>

Myroslava HORIACHA^{1,2}, Galyna NYCHYPORUK¹, Yaroslav GALADZHUN³,
Rainer PÖTTGEN², Vasyl ZAREMBA¹

CRYSTAL STRUCTURE OF PHASES FROM GdNiIn_{1-x}Al_x SOLID SOLUTION

¹*Inorganic Chemistry Department, Ivan Franko National University of Lviv,
Kyryla i Mefodiya Str., 6, 79005 Lviv, Ukraine
e-mail: myroslava.horyacha@lnu.edu.ua*

²*Institut für Anorganische Chemie, Universität Münster,
Corrensstraße 30, D-48149, Germany*

³*Department of Life Safety, Ivan Franko National University of Lviv,
Doroshenka Str., 41, 7900 Lviv, Ukraine*

The two phases within a continuous solid solution between the GdNiIn and GdNiAl compounds were synthesized and their crystal structures were determined on the basis of X-ray single crystal data: GdNiAl (ZrNiAl type, $P-62m$, $a = 0.70200(5)$, $c = 0.39148(1)$ nm, $R_1 = 0.0091$, $wR_2 = 0.0202$) and GdNiIn_{0.48(1)}Al_{0.52(1)} (ZrNiAl type, $P-62m$, $a = 0.72500(5)$, $c = 0.38532(1)$ nm, $R_1 = 0.0151$, $wR_2 = 0.0323$). Features of the structure were briefly discussed.

Keywords: Aluminum, Indium, single crystal, crystal structure.

Introduction

Ternary RENiIn and RENiAl compounds with a hexagonal ZrNiAl-type structure are characterized by complex magnetic behaviour over a wide temperature range [1–4]. The relationship between magnetic properties and the electronic structure of intermetallic compounds with ZrNiAl-type structure was analyzed and confirmed by magnetometric, neutron diffraction, and spectroscopic measurements [5]. The GdNiAl compound is characterized by a complex magnetic structure with three transitions (ferromagnetic at 60 K and two antiferromagnetic orderings at 31 and 14 K) [6–8]. Interesting physical properties show the GdNiIn compound [9–11]. The magnetic properties of several (Gd_{1-x}Er_x)NiAl alloys were undertaken using magnetic and heat capacity measurements in an attempt to understand the table-like magnetocaloric effect previously observed in (Gd_{0.54}Er_{0.46})NiAl [12].

The formation of continuous solid solutions between isostructural RENiIn and RENiAl ($RE = Ce, Y, Gd, Tb$) compounds was observed [13–18]. Here we present the results of the crystal structure determination of some phases of the GdNiIn_{1-x}Al_x solid solution [16] for the single crystals from alloys with two different compositions.

Experimental details

At the first step, ingots of gadolinium (Smart Elements), nickel wire (Chempur), indium tear drops (Smart Elements), and aluminum lumps (Smart Elements), all metals with purities more than 99.9% were melted in arc-furnace under argon atmosphere. Further arc-melted alloys with composition GdNiAl and $\text{GdNiIn}_{0.5}\text{Al}_{0.5}$ were placed in small tantalum tubes and arc-welded under an argon pressure of about 600 mbar for single crystal growing. The tube was enclosed in an evacuated silica ampoule, and the sample was heated in a Naberterm HTCT 01/16 furnace. At first, samples were heated to 1373 K within 6 h and held at that temperature for 2 h, cooled at a rate of 3 K/h to 1173 K and held at that temperature for 6 h. Finally, the samples were cooled to room temperature within 20 h. Irregularly shaped crystal fragments were selected from the crushed samples and were first investigated with a Buerger precession camera with white molybdenum radiation to check their quality for intensity data collection. Intensity data were collected at room temperature with a STOE IPDS II diffractometer (graphite monochromatized Mo K_{α} -radiation; oscillation mode, room temperature). The crystal structure was solved and refined with programs from the JANA 2006 [19]. The measured crystals were analyzed semi-quantitatively with a Zeiss EVO MA10 scanning electron microscope. The experimentally determined element ratio for the GdNiAl : 34(2) at.% Gd, 32(2) at.% Ni, 34(2) at.% Al, and for the $\text{GdNiIn}_{0.48(1)}\text{Al}_{0.52(1)}$: 35(2) at.% Gd, 30(2) at.% Ni, 15(2) at.% In, 20(2) at.% Al.

Results and discussion

GdNiIn and GdNiAl compounds form a continuous solid solution with the ZrNiAl -type structure, described by X-ray powder diffraction [16]. To confirm these results crystal structure of GdNiAl and $\text{GdNiIn}_{0.48(1)}\text{Al}_{0.52(1)}$ phases were synthesized and refined from single crystal data. Structure refinement (was performed within the ZrNiAl -type structure model) for $\text{GdNiIn}_{0.48(1)}\text{Al}_{0.52(1)}$ phase showed that $3g$ position is occupied by a mixture of In/Al atoms. An increase in the content of the larger atoms of In in this position leads to a rise of the a lattice parameter and a decrease of the c parameter: $a = 0.72500(5)$, $c = 0.38532(1)$ nm. For both structures all positions are fully occupied. Details on the crystallographic data and the structure refinements are listed in Table 1. Atomic coordinates and anisotropic displacement parameters in the refined structures are listed in Table 2 and interatomic distances - in Table 3.

Representatives of the ZrNiAl -type structure are built up of two types of layers. The first one contains the Gd atoms located at the Wyckoff positions $3f(x, 0, 0)$ and one of the Ni atoms at the $1a(0, 0, 0)$ position (Fig. 1, a). The second layer is formed of the p -element (Al, In or Al/In) atoms at the positions $3g(x, 0, 1/2)$ and Ni atoms located at $2d(2/3, 1/3, 1/2)$ position (Fig. 1, b). Increasing of interatomic distances with Al substitution by In is expected. However we observed that one Gd–M distance of 0.3126 nm (Fig. 2, a) is even shorter than the Gd–Al distance of 0.3131 nm (Fig. 2, b). This fact can, to a certain extent, explain the decrease in the parameter c of the unit cell in the phases of the $\text{GdNiIn}_{1-x}\text{Al}_x$ solid solution [16] and solid solutions in other related systems, and also indicates the strengthening of the interaction in Gd–M pairs.

The unit-cell parameters of phases within the $\text{GdNiIn}_{1-x}\text{Al}_x$ solid solution [16] change proportionally to the sizes of In and Al atoms [21], as well as to the unit-cell parameters of ternary compounds GdNiIn and GdNiAl . The same regularity can be observed in the phases of the $\text{GdCuIn}_{1-x}\text{Al}_x$ solid solution [23] (Table 4).

Table 1

Crystallographic data and structure refinement for GdNiAl and GdNiIn_{0.48(1)}Al_{0.52(1)}
ZrNiAl-type structure, space group *P-62m*, Z = 3

| Formula | GdNiAl | GdNiIn _{0.48(1)} Al _{0.52(1)} |
|---|-------------------------|---|
| Pearson symbol | <i>hP9</i> | |
| <i>a</i> = 0.70200(5) | | <i>a</i> = 0.72500(5) |
| Lattice parameters, nm | <i>c</i> = 0.39148(1) | <i>c</i> = 0.38532(1) |
| | <i>V</i> = 0.16708(2) | <i>V</i> = 0.17540(2) |
| Radiation; λ , nm | Mo $K\alpha$; 0.071073 | |
| Temperature, K | | 293 |
| Density calcd., g/cm ³ | 7.2431 | 8.1043 |
| Absorption coeff. nm ⁻¹ · 10 ⁶ | 38.562 | 40.549 |
| <i>F</i> (000) | 315 | 367 |
| θ range | 3.36–35.01 | 3.24–34.79 |
| <i>hkl</i> range | ±11, ±11, -5/6 | -9/11, ±11, ±6 |
| No. of reflections | 6114 | 4361 |
| Independent reflections/parameters | 305/15 | 316/16 |
| Reflections with <i>I</i> > 2 <i>σ</i> (<i>I</i>) | 298 | 309 |
| Goodness-of-fit <i>F</i> ² | 0.83 | 1.16 |
| <i>R</i> ₁ / <i>wR</i> ₂ for <i>I</i> > 2 <i>σ</i> (<i>I</i>) | 0.0086/0.0201 | 0.0139/0.0320 |
| <i>R</i> ₁ / <i>wR</i> ₂ for all data | 0.0091/0.0202 | 0.0151/0.0323 |
| Flack parameter | -0.02(2) | 0.10(2) |
| Largest diff. peak/hole, e/nm · 10 ³ | 0.45/-0.50 | 0.71/-0.84 |

Table 2

**Atomic coordinates and anisotropic displacement parameters
in the GdNiAl and GdNiIn_{0.48(1)}Al_{0.52(1)} structures**

| Atom | Wyck. | <i>x</i> | <i>y</i> | <i>z</i> | <i>U</i> _{eq} · 10 ² , nm ² |
|---|------------|------------------------|------------------------|------------------------|--|
| GdNiAl | | | | | |
| Gd | 3 <i>f</i> | 0.41778(3) | 0 | 0 | 0.0088(1) |
| Ni1 | 1 <i>a</i> | 0 | 0 | 0 | 0.0098(2) |
| Ni2 | 2 <i>d</i> | 2/3 | 1/3 | 1/2 | 0.0117(2) |
| Al | 3 <i>g</i> | 0.7658(2) | 0 | 1/2 | 0.0093(3) |
| Atom | | | | | |
| | | <i>U</i> ₁₁ | <i>U</i> ₂₂ | <i>U</i> ₃₃ | <i>U</i> ₁₂ |
| Gd | | 0.0085(1) | 0.0084(1) | 0.0095(1) | 0.0042(1) |
| Ni1 | | 0.0105(1) | 0.0105(2) | 0.0085(4) | 0.0052(1) |
| Ni2 | | 0.0125(1) | 0.0125(1) | 0.0101(3) | 0.0062(1) |
| Al | | 0.0087(4) | 0.0098(5) | 0.0098(4) | 0.0049(2) |
| GdNiIn_{0.48(1)}Al_{0.52(1)} | | | | | |
| Gd | 3 <i>f</i> | 0.41510(5) | 0 | 0 | 0.0122(1) |
| Ni1 | 1 <i>a</i> | 0 | 0 | 0 | 0.0207(5) |
| Ni2 | 2 <i>d</i> | 2/3 | 1/3 | 1/2 | 0.0146(3) |
| <i>M</i> | 3 <i>g</i> | 0.75464(11) | 0 | 1/2 | 0.0119(3) |
| Atom | | | | | |
| | | <i>U</i> ₁₁ | <i>U</i> ₂₂ | <i>U</i> ₃₃ | <i>U</i> ₁₂ |
| Gd | | 0.0130(1) | 0.0120(2) | 0.0114(1) | 0.0060(1) |
| Ni1 | | 0.0218(6) | 0.0218(6) | 0.0187(8) | 0.0109(3) |
| Ni2 | | 0.0155(4) | 0.0155(4) | 0.0126(5) | 0.0078(2) |
| <i>M</i> | | 0.0108(4) | 0.0120(4) | 0.0133(4) | 0.0060(2) |

M = 0.48(1) In + 0.52(1) Al

Table 3

**Interatomic distances (δ , nm) and CN of atoms in the
GdNiAl and GdNiIn_{0.48(1)}Al_{0.52(1)} structures**

| Atom | δ , nm | CN | Atom | δ , nm | CN | |
|--------|---------------|------------|-------|---------------|---|------------|
| GdNiAl | | | | | GdNiIn _{0.48} Al _{0.52} | |
| Gd | 4Ni2 | 0.28757(1) | 15 | Gd | 4Ni2 | 0.29103(1) |
| | Ni1 | 0.29329(3) | | | Ni1 | 0.30094(4) |
| | 2Al | 0.3131(1) | | | 2M | 0.31260(7) |
| | 4Al | 0.32115(9) | | | 4M | 0.32525(6) |
| | 4Gd | 0.36495(2) | | | 4Gd | 0.37786(2) |
| Ni1 | 6Al | 0.25561(5) | 9 | Ni1 | 6M | 0.26223(5) |
| | 3Gd | 0.29328(2) | | | 3Gd | 0.30093(3) |
| Ni2 | 3Al | 0.27546(4) | 9 | Ni2 | 3M | 0.27907(6) |
| | 6Gd | 0.28758(1) | | | 6Gd | 0.29103(1) |
| Al | 2Ni1 | 0.25562(9) | M^* | 2Ni1 | 0.26223(5) | |
| | 2Ni2 | 0.2755(1) | | | 2Ni2 | 0.27907(6) |
| | 2Al | 0.2848(2) | | | 2M | 0.3081(1) |
| | 2Gd | 0.3131(1) | | | 2Gd | 0.31258(7) |
| | 4Gd | 0.32115(2) | | | 4Gd | 0.32525(2) |

* $M = 0.48(1)$ In + 0.52(1) Al




Fig. 1. Type of the layers in the GdNiIn_{0.48}Al_{0.52} structure.




Fig. 2. The unit cell of GdNiIn_{0.48}Al_{0.52} (a) and GdNiAl (b) along the ab projection.

Table 4

**Cell parameters of the phases in $GdTIn_{1-x}Al_x$ ($T = Ni, Cu$) solid solutions
(ZrNiAl-type structure, space group $P-62m$)**

| Phase | a , nm | c , nm |
|--|------------------|------------------|
| GdNiIn ^b [9] | 0.7452 | 0.3837 |
| GdNiIn _{0.5} Al _{0.5} ^b [this work] | 0.7250 | 0.3853 |
| GdNiIn _{0.3} Al _{0.7} ^a [16] | 0.7153 | 0.4076 |
| GdNiAl ^b [7] [this work] | 0.7021 0.7020 | 0.3921 0.3915 |
| GdCuIn ^a [22] | 0.7470 | 0.3993 |
| GdCuIn _{0.7} Al _{0.3} ^b [23] | 0.7376 | 0.3989 |
| GdCuIn _{0.3} Al _{0.7} ^a [16] | 0.7145 | 0.4078 |
| GdCuAl ^b [23] | 0.7054 | 0.4062 |

^aLattice parameters from powder data

^bLattice parameters from single crystal data

Conclusions

Single crystals of the GdNiAl and GdNiIn_{0.48(1)}Al_{0.52(1)} phases were synthesized using a special technique, and their crystal structures, which are representatives of the ZrNiAl-type structure, were refined. The replacement of aluminum atoms by indium atoms in the structure GdNiIn_{0.48(1)}Al_{0.52(1)} occurs in position 3g ($x 0 1/2$) of space group $P-62m$, which is characterized by a change in the coordinates of atoms along the a and b directions. The unit-cell parameters of phases within the GdNiIn_{1-x}Al_x solid solution change proportionally to the sizes of In and Al atoms, as well as to the unit-cell parameters of the ternary compounds GdNiIn and GdNiAl.

This work was supported by the DAAD foundation (research scholarship to MH).

REFERENCES

1. Gupta S., Suresh K.G. Review on magnetic and related properties of RTX compounds. J. Alloys Compd. 2015. Vol. 618. P. 562–606. (<https://doi.org/10.1016/j.jallcom.2014.08.079>).
2. Ferro R., Marazza R., Rambaldi G. Equiatomic ternary phases in the alloys of the rare earths with indium and nickel or palladium. Z. Metallkd. 1974. Vol. 65. P. 37–39. (<https://doi.org/10.1515/ijmr-1974-650106>).
3. Kalychak Ya.M., Zaremba V.I., Pöttgen R., Lukachuk M., Hoffmann R.-D. Rare Earth-Transition Metal-Indides. In: K.A. Gschneidner, Jr., J.-C. Bünzli, V. K. Pecharsky (Eds.). Handbook on the Physics and Chemistry of Rare Earths. Elsevier, Amsterdam. 2005. Vol. 34. P. 1–133. ([https://doi.org/10.1016/S0168-1273\(04\)34001-8](https://doi.org/10.1016/S0168-1273(04)34001-8)).
4. Oesterreicher H. Structural and magnetic studies on rare-earth compounds RNiAl and RCuAl. J. Less-Common Met. 1973. Vol. 30. P. 225–236. ([https://doi.org/10.1016/0022-5088\(73\)90109-4](https://doi.org/10.1016/0022-5088(73)90109-4)).
5. Godnek Ł., Żukowski J., Balanda M., Kaczorowski D., Szytuła A. Magnetism and electronic structures of hexagonal 1:1:1 rare earth-based intermetallic compounds. Mater. Sci.-Pol. 2008. Vol. 26(4). P. 815–820.

6. Merlo F., Cirafici S., Canepa F. Structural anomaly in GdNiAl: a crystallographic, electric and magnetic investigation. *J. Alloys Compd.* 1998. Vol. 266. P. 22–25. ([https://doi.org/10.1016/S0925-8388\(97\)00505-7](https://doi.org/10.1016/S0925-8388(97)00505-7)).
7. Jarosz J., Talik E., Mydlarz T., Kusz J., Böhm H., Winiarski A. Crystallographic, electronic structure and magnetic properties of the GdTAl; $T = \text{Co, Ni and Cu}$ ternary compounds. *J. Magn. Magn. Mater.* 2000. Vol. 208. P. 169–180. ([https://doi.org/10.1016/S0304-8853\(99\)00592-2](https://doi.org/10.1016/S0304-8853(99)00592-2)).
8. Danis S., Javorsky P., Rafaja D. Magneto-crystalline anisotropy in TbPdIn, DyNiAl and GdNiAl studied by using X-ray powder diffraction at low temperatures. *J. Alloys Compd.* 2002. Vol. 345. P. 10–15. ([https://doi.org/10.1016/S0925-8388\(02\)00332-8](https://doi.org/10.1016/S0925-8388(02)00332-8)).
9. Merlo F., Fornasini M.L., Cirafici S., Canepa F. Physical properties of GdNiIn. *J. Alloys Compd.* 1998. Vol. 267. P. L12–L13. ([https://doi.org/10.1016/S0925-8388\(97\)00541-0](https://doi.org/10.1016/S0925-8388(97)00541-0)).
10. Canepa F., Napoletano M., Palenzona A., Merlo F., Cirafici S. Magnetocaloric properties of GdNiGa and GdNiIn intermetallic compounds. *J. Phys. D: Appl. Phys.* 1999. Vol. 32. P. 2721–2725. (<https://doi.org/10.1088/0022-3727/32/21/303>).
11. Tyvanchuk Y.B., Kalychak Y.M., Gondek L., Rams M., Szytula A., Tomkowicz Z. Magnetic properties of $R\text{Ni}_{1-x}\text{In}_{1+x}$ ($R = \text{Gd-Er}$) compounds. *J. Magn. Magn. Mater.* 2004. Vol. 277. P. 368–378. (<https://doi.org/10.1016/j.jmmm.2003.11.018>).
12. Korte B.J., Pecharsky V.K., Gschneidner K.A., Jr. The correlation of the magnetic properties and the magnetocaloric effect in $\text{Gd}_{1-x}\text{Er}_x\text{NiAl}$ alloys. *J. Appl. Phys.* 1998. Vol. 84. P. 5677. (<https://doi.org/10.1063/1.368830>).
13. Zaremba N., Nychyporuk G., Schepilov Yu., Panakhyd O., Muts I., Hlukhy V., Pavlyuk V. The CeNiIn_{1-x}M_x ($M = \text{Al, Ga}$) systems at 873 K. *Ukr. Chem. J.* 2018. Vol. 84(12). P. 76–84 (in Ukrainian).
14. Horiacha M., Savchuk I., Nychyporuk G., Serkiz R., Zaremba V. The YNiIn_{1-x}M_x ($M = \text{Al, Ga, Sb}$) systems. *Visnyk Lviv Univ. Ser. Chem.* 2018. Vol. 59(1). P. 67–75. (<https://doi.org/10.30970/vch.5901.067>).
15. Horiacha M., Nychyporuk G., Bönnighausen J., Stegemann F., Pavlyuk V., Pöttgen R., Zaremba V. Structure and properties of phases from solid solutions YTIn_{1-x}Al_x ($T = \text{Ni and Cu}$). *Z. Kristallogr.* 2023. Vol. 238(1–2). P. 17–25. (<https://doi.org/10.1515/zkri-2022-0052>).
16. Horiacha M., Zinko L., Nychyporuk G., Serkiz R., Zaremba V. The GdTIn_{1-x}M_x ($T = \text{Ni, Cu}; M = \text{Al, Ga}; 0 < x < 1$) systems. *Visnyk Lviv Univ. Ser. Chem.* 2017. Vol. 58(1). P. 77–85 (in Ukrainian).
17. Horiacha M., Halyatovskii B., Horiacha S., Nychyporuk G., Pöttgen R., Zaremba V. The TbNiIn_{1-x}M_x ($M = \text{Al, Ge, Sb}$) systems. *Visnyk Lviv Univ. Ser. Chem.* 2020. Vol. 61(1). P. 52–62 (in Ukrainian). (<https://doi.org/10.30970/vch.6101.052>).
18. Klípera M., Javorský P., Daniš S. The change of anisotropy in TbNi(Al, In) compounds studied by low temperature X-ray diffraction. *J. Phys. Conf. Ser.* 2011. Vol. 303. P. 012031(6). (<https://doi.org/10.1088/1742-6596/303/1/012031>).
19. Petříček V., Dušek M., Palatinus L. Crystallographic Computing System JANA 2006: General features. *Z. Kristallogr.* 2014. Vol. 229(5). P. 345–352. (<https://doi.org/10.1515/zkri-2014-1737>).
20. Krypyakevych P.I., Markiv V.Ya., Mel'nyk E.V. The crystal structure of the compounds ZrNiAl , ZrCuGa and their analogue. *Dopov. AN URSR, Ser. A.* 1967. P. 750–753 (in Ukrainian).
21. Emsley J. The Elements: 2-nd ed. Oxford: ClarendonPress, 1991. 251 p.
22. Szytula A., Tyvanchuk Y.B., Jaworska Golab T., Zarzycki A., Kalychak Y.M., Gondek L., Stüsser N. Magnetic properties of the $RCuIn$ ($R = \text{Ce, Nd, Gd, Tb, Dy, Ho, Er}$) and $R_2\text{CuIn}_3$ ($R = \text{Ce, Gd, Tb, Dy}$) compounds. *Chem. Met. Alloys.* 2008. Vol. 1. P. 97–101. (<https://doi.org/10.30970/cma1.0012>).

23. *Horiacha M., Nyhyporuk G., Pöttgen R., Zaremba V.* The crystal structure of the phases in the $\text{GdCuIn}_{1-x}\text{Al}_x$ system. Proc. Shevchenko Sci. Soc. Chem. Sci. 2019. Vol. LVI. P. 122–129. (in Ukrainian). (<https://doi.org/10.37827/ntsh.chem.2019.56.122>).

РЕЗЮМЕ

Мирослава ГОРЯЧА^{1,2}, Галина НИЧИПОРУК¹, Ярослав ГАЛАДЖУН³,
Райнер ПЬОТТГЕН², Василь ЗАРЕМБА¹

КРИСТАЛІЧНА СТРУКТУРА ФАЗ ТВЕРДОГО РОЗЧИНУ $\text{GdNiIn}_{1-x}\text{Al}_x$

¹Львівський національний університет імені Івана Франка,
 вул. Кирила і Мефодія, 6, 79005 Львів, Україна
 e-mail: myroslava.horyacha@lnu.edu.ua

²Університет Мюнстера,
 Корренштрассе, 30, D-48149 Мюнстер, Німеччина

³Львівський національний університет імені Івана Франка,
 вул. Дорошенка, 41, 79000 Львів, Україна

Неперервний твердий розчин зі структурою типу ZrNiAl , який формується на основі сполук GdNiIn та GdNiAl , раніше досліджений методом рентгенівської порошкової дифракції. Для підтвердження цих результатів синтезовано монокристали фаз GdNiAl і $\text{GdNiIn}_{0.48(1)}\text{Al}_{0.52(1)}$ та уточнено їхню кристалічну структуру.

Попередньо синтезовані методом електродугового сплавлення зразки складів GdNiAl та $\text{GdNiIn}_{0.5}\text{Al}_{0.5}$ піддали спеціальній термічній обробці. У результаті одержали монокристали неправильної форми з металевим біском, які протестували методом Лауе (прецесійна камера Бюргера, Mo К-проміння) та підтвердили гексагональну сингонію для них. Якісний та кількісний склад кристалів підтверджено результатаами EDX аналізу (скануючий електронний мікроскоп Zeiss EVO MA10). Розшифрування й уточнення кристалічної структури обох фаз виконано в рамках моделі структурного типу ZrNiAl із використанням пакета програм JANA 2006 на основі масивів експериментальних відбитків hkl , одержаних на дифрактометрі Stoe IPDS II (Mo $K\alpha$ -проміння): GdNiAl (ZrNiAl , $P-62m$) – $a = 0,70200(5)$, $c = 0,39148(1)$ нм, $R_1 = 0,0091$, $wR_2 = 0,0202$ та $\text{GdNiIn}_{0.48(1)}\text{Al}_{0.52(1)}$ (ZrNiAl , $P-62m$) – $a = 0,72500(5)$, $c = 0,38532(1)$ нм, $R_1 = 0,0151$, $wR_2 = 0,0323$.

Атоми статистичної суміші In/Al займають ПСТ $3g$ ($x, 0, 1/2$) у структурі фази $\text{GdNiIn}_{0.48(1)}\text{Al}_{0.52(1)}$. Міжатомні віддалі $\text{Gd}-M$ у структурі цієї фази є коротшими, ніж у тернарній сполуці GdNiAl . Подібні закономірності простежуються у системі $\text{GdCuIn}_{1-x}\text{Al}_x$.

Ключові слова: алюміній, індій, метод монокристала, кристалічна структура.

Стаття надійшла: 27.05.2023.
 Після доопрацювання: 02.08.2023.
 Прийнята до друку: 29.09.2023.